



| LAST-A-FOAM® TF-6070-10 FLEXIBLE POLYURETHANE FOAM | | | |
|--|---------|--------|-------------|
| Property | English | Metric | Test Method |
| Density (pcf) (kg/m ³) | 10.0 | 160 | ASTM D-3574 |
| Load Deflection (psi) (kPa) | | | ASTM D-3574 |
| @ 75°F: Stress at 10% | 7.9 | 54 | |
| @ 75°F: Stress at 50% | 20 | 138 | |

Values shown are average values determined from laboratory tests. Material properties are customizable. Please contact the Sales Department to set specifications.

10/17/2012

GENERAL PLASTICS MANUFACTURING COMPANY
4910 BURLINGTON WAY
TACOMA, WA 98409
phone (253) 473-5000 fax (253) 473-5104
e-mail: sales@generalplastics.com
website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.